

# Ferro Tungsten

26	55.845	74	183.84
<b>Fe</b>	<sup>5</sup> D <sub>4</sub> 1,83	<b>W</b>	<sup>5</sup> D <sub>0</sub> 2,36
<b>Iron</b>		<b>Tungsten</b>	
7,874	7,9024	19,25	7,8640
1538	2861	3422	5555
(m) 126	BCC	(m) 139	BCC
[Ar] 3d <sup>6</sup> 4s <sup>2</sup> +2,3		[Xe] 4f <sup>14</sup> 5d <sup>4</sup> 6s <sup>2</sup> +2,3,4,5,6	

## Typical content (% w/w)

Element	Content
<b>W</b>	75 – 78
<b>C</b>	0,20 max.
<b>Cu</b>	0,15 max.
<b>P</b>	0,05 max.
<b>Sb</b>	0,05 max.
<b>Si</b>	1,5 max.
<b>Mn</b>	0,50 max.
<b>S</b>	0,08 max.
<b>As</b>	0,10 max.
<b>Sn</b>	0,08 max.

## Size

0 to 10 mm.  
10 to 50 mm.  
10 to 100 mm.

## Packaging

Drums with 250 Kg  
Drums with 500 Kg.  
Drums with 1000 Kg.  
Other packaging available according to product specifications customer.

## Delivery time

Prompt.

## Remarks

All our products shall be labelled with product name, reference number and net weight. Each delivery is accompanied by a certificate of analysis and the delivery note.

### COMETAL, S.A.

- C/José Lázaro Galdiano 4
- 28036 Madrid (Spain)
- Ph: +34 91 4585980
- Fax: +34 91 4585987

- cometal@cometalsa.com
- www.cometalsa.com
- VAT Nr ESA28117026

